

Abstract

An insulating film is formed on a semiconductor base material, the insulating film being predominantly composed of organic siloxane and containing an organic component which has
5 no chemical bond to the organic siloxane. Plasma treatment is applied to the insulating film to remove the organic component and form a modifying layer on a surface of the insulating film.